



ATTORNEY DOCKET NO.: 92/F 294 (9086\*85)

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

ANDREAS WINTER ET AL.

SERIAL NO: 08/120,105

: ART UNIT: 1713

FILED: SEPTEMBER 10, 1993

: EXAMINER: WILSON

FOR: A PROCESS FOR THE PREPARATION OF  
POLYOLEFIN MOLDING COMPOSITIONS  
HAVING A BROAD MELTING RANGE

: BOX AF

Asst. Commissioner for Patents  
Washington, D.C. 20231

I HEREBY CERTIFY THAT THIS CORRESPONDENCE IS BEING DEPOSITED WITH THE UNITED STATES POSTAL SERVICE AS  
FIRST-CLASS MAIL IN AN ENVELOPE ADDRESSED TO: ASST. COMMISSIONER FOR PATENTS, WASHINGTON D.C. 20231 ON  
THIS 29<sup>th</sup> DAY OF May 2002. BY: J. Ryan Ferry

AMENDMENT AFTER FINAL

Sir:

In response to the Office Action mailed March 29, 2002, please amend the above-identified application as follows.

IN THE CLAIMS

Please amend claims 17 and 22 as follows:

17. A process for the preparation of a polyolefin molding composition comprising at least two polyolefinic components, wherein the composition is characterized by a broad, bimodal, or multimodal melting range in a DSC spectrum determined with a heating/cooling rate of 20° C/min wherein the peak in the melting range has a maximum and can be bimodal or multimodal and the maximum of the peak in the melting range is between 120 and 165°C, the half-intensity width of the melting peak is broader than 10°C and the width determined at quarter peak height is greater than 15°C, wherein such process comprises the direct polymerization of propylene or copolymerization of propylene with olefins of the formula  $R^aCH = CHR^b$ , in which  $R^a$  and  $R^b$  are identical or different and are a hydrogen atom or an alkyl radical having 2 to 14 carbon atoms wherein the polymerized ethylene content of the resulting polyolefin composition is from 0 to 2.5% by weight, to at least two polyolefins of different melting points, wherein the melting points of the

RECEIVED  
JUN 12 2002  
TC 1700

AP  
1709  
#188/J  
(NE)